



F00952EQ

High Density Polyethylene for Blown film

Product Description

F00952EQ is high molecular weight high density polyethylene copolymer grade specifically designed for blown film applications. The design of the product, molecular architecture and density gives a unique combination of easy extrusion and high melt strength with strong physical properties which makes it suitable for producing very thin films with excellent strength and rigidity.

Typical Applications

F00952EQ resin is recommended for blown film extrusion. This product is suggested for the manufacture of high strength grocery sacks, shopping bags and high quality thin films for multi wall sack liners and replacement for thin paper products.

Typical data

Properties	Unit	Value ⁽¹⁾	ASTM Method
Resin Properties			
Melt Flow Rate @ 190°C & 2.16 kg load	g/10 min.	0.05	D 1238
@ 190°C & 21.6 kg load		8.5	
Density @ 23°C	kg/m ³	952	D 1505
Mechanical Properties⁽²⁾			
Tensile Strength @ break, MD	MPa	66	D 882
TD		64	
Tensile Elongation @ break, MD	%	400	D 882
TD		550	
Tensile Strength @ yield, MD	MPa	33	D 882
TD		40	
1% Secant Modulus, MD	MPa	1250	D 882
TD		1500	
Dart Impact Strength	g	180	D 1709
Elmendorf Tear Strength, MD	g	12	D 1922
TD		60	
Thermal Properties			
Vicat Softening Point	°C	125	D 1525

(1) Typical values; not to be construed as specification limits.

(2) Properties are based on 15 µm film produced at 4 BUR using 100% F00952EQ.

Processing Conditions

Melt Temperature: 200 - 235°C

Frost Line Height: 6 - 8 times die Ø

BUR: 3 - 5

Food Regulation

F00952EQ is suitable for Food contact application. Detailed information is provided in relevant Material Safety Datasheet and for additional specific information please contact SABIC local representative for certificate.

Storage and Handling

Polyethylene material should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

Saudi Basic Industries Corporation, P.O.Box 5101, Riyadh 11422, Kingdom of Saudi Arabia
Tel: 966 1 2258000
Fax: 966 1 2259000

Technical Marketing
Tel: 966 1 2659166
Fax: 966 1 2659244
Toll-free 800 1245577

PE Sales:
Fax: 966 1 2258760
Website: www.sabic.com

NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.