



Product Description

General purpose Polystyrene 500 is manufactured by continuous mass polymerization of styrene monomer. It is a crystal-like, hard and brittle polymer with good flow properties and excellent clarity. It is designed for medium and thin wall thickness articles and gives broad processing window for molding applications.

Typical Applications

It is recommended for the manufacture of packaging items such as plastic boxes and typical applications include cutlery, tumblers, office stationery items, jewelry boxes, medical supplies or any clear injection molded items.

Typical data

Properties	Unit	Value ⁽¹⁾	ASTM Method
Resin Properties			
Melt Flow Rate @ 200°C & 5 kg load	g/10 min.	13	D-1238
Density @ 23°C	kg/m ³	1050	D-792
Bulk Density (Method B)	kg/m ³	600	D-1895
Mechanical Properties ⁽²⁾			
Tensile Strength	MPa	40	D-638
Tensile Elongation	%	1.8	D-638
Tensile Modulus	MPa	3334	D-638
Flexural Strength	MPa	71	D-790
Flexural Modulus	MPa	3041	D-790
Thermal Properties ⁽²⁾			
Vicat Softening Point (Rate A, 1 Kg/50°C)	°C	97	D-1525
Heat Deflection Temperature (Method B, 1.8 MPa, Annealed)	°C	94	D-648

(1) Typical values; not to be construed as specification limits.

(2) Based on injection molded specimens.

Processing Conditions

Typical temperature (°C) profile for injection grade 500:

Throat	Feed	Transition	Metering	Die
Ambient	160	190	210	205

Food Regulation

500 is suitable for Food contact application. Detailed information is provided in relevant Material Safety Datasheet and for additional specific information please contact SABIC local representative for certificate.

Storage and Handling

Polystyrene resin should be stored to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PS resin within 6 months after delivery.

Saudi Basic Industries Corporation, P.O.Box 5101, Riyadh 11422, Kingdom of Saudi Arabia
Tel: 966 1 2258000
Fax: 966 1 2259000

Technical Marketing
Tel: 966 1 2659166
Fax: 966 1 2653544
Toll-free 800 1245577

PS Sales:
SABIC Petrochemicals Ltd Istanbul
T : +90 216 571 75 00

Website: www.sabic.com

NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.