



HP7022

Low Density Polyethylene for Injection Molding

Product Description

HP7022 is Low Density Polyethylene offering a unique combination of consistent processability, flexibility and toughness. Articles manufactured from HP7022 exhibit excellent impact strength, low shrinkage and good gloss.

Typical Applications

HP7022 is intended for producing flexible injection molded articles. It is particularly suited for closures, caps, lids, houseware articles, toys and as base resin for masterbatch.

Typical data

Properties	Unit	Value ⁽¹⁾	ASTM Method
Resin Properties			
Melt Flow Rate @ 190°C & 2.16 kg load	g/10 min.	7	D 1238
Density @ 23°C	kg/m ³	922	D 1505
Mechanical Properties⁽²⁾			
Tensile Strength @ break	MPa	11	D 638
Tensile Elongation @ break	%	88	D 638
Tensile Strength @ yield	MPa	10	D 638
1% Secant Modulus	MPa	170	D 638
Izod Impact @ 23°C	J/m	475	D 256
Hardness (Shore D)	-	50	D 2240
Thermal Properties⁽²⁾			
Vicat Softening Point	°C	86	D 1525
Brittleness Temperature	°C	<-75	D 746

(1) Typical values; not to be construed as specification limits.

(2) Based on injection molded specimens

Processing Conditions

Typical molding conditions for HP7022 are:

Barrel temperature: 180 - 210°C (356 - 410°F)

Mold temperature: 20 - 40°C (70 - 104°F)

Food Regulation

HP7022 is suitable for Food contact application. Detailed information is provided in relevant Material Safety Datasheet and for additional specific information please contact SABIC local representative for certificate.

Storage and Handling

Polyethylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

Saudi Basic Industries Corporation, P.O.Box 5101, Riyadh 11422, Kingdom of Saudi Arabia

Tel: 966 1 2258000

Fax: 966 1 2259000

Technical Marketing

Tel: 966 1 2659166

Fax: 966 1 2653544

Toll-free 800 1245577

PE Sales:

Fax: 966 1 2258760

Website: www.sabic.com

NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.