



PP 500U

PP Homopolymer for Raffia applications

Product Description

PP 500U is specially developed for producing stretched tapes offering medium level of UV protection.

PP 500U has following features:

- Consistent processability
- Easy orientation
- Low water carry over
- Good mechanical properties
- UV stabilized

Typical Applications

PP 500U can be used for producing woven bags, flexible intermediate bulk containers, ropes & twines and geotextiles. For specific end-use applications additional UV stabilizer may be required.

Typical data

Properties	Unit	Value ⁽¹⁾	ASTM Method
Resin Properties			
Melt Flow Rate @ 230°C & 2.16 kg load	g/10 min.	3	D 1238
Density @ 23°C	kg/m ³	905	D 792
Mechanical Properties ⁽²⁾			
Tensile Strength @ Yield	MPa	35	D 638
Tensile Elongation @ Yield	%	12	D 638
Flexural Modulus (1% Secant)	MPa	1480	D 790A
Notched Izod Impact Strength @ 23°C	J/m	35	D 256
Rockwell Hardness, R-Scale	-	102	D 785
Thermal Properties ⁽²⁾			
Vicat Softening Point	°C	155	D 1525B
Heat Deflection Temperature @ 455 KPa	°C	100	D 648

(1) Typical values; not to be construed as specification limits.

(2) Based on injection molded specimens.

Processing Conditions

Barrel temperature range: 235 - 250°C

Food Regulation

PP 500U is not intended for Food contact application. Detailed information is provided in relevant Material Safety Datasheet and for additional specific information please contact SABIC local representative for certificate.

Storage and Handling

PP resin should be stored to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PP resin within 6 months after delivery.

Saudi Basic Industries Corporation, P.O.Box 5101, Riyadh 11422, Kingdom of Saudi Arabia

Tel: 966 1 2258000

Fax: 966 1 2259000

Technical Marketing

Tel: 966 1 2659166

Fax: 966 1 2653544

Toll-free 800 1245577

PP Sales:

Fax: 966 1 2258771

Website: www.sabic.com

NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.