

# LEXANT™ FR RESINS FL910

REGION AMERICAS

## DESCRIPTION

LEXANT™ FL910 resin is a 10% glass fiber filled foamable polycarbonate. Flame retardant, UL94 V0 and 5VA rated. High flexural strength and modulus. Injection moldable.

## TYPICAL PROPERTY VALUES

Revision 20201125

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
FOAM - MECHANICAL 6.4 mm Wt Reduction	10	%	-
Tensile Stress, yield, 6.35 mm	52	MPa	ASTM D638
Tensile Strain, break, 6.35 mm	4.8	%	ASTM D638
Tensile Modulus, 6.4 mm	3170	MPa	ASTM D638
Flexural Stress, yield, 6.4 mm	89	MPa	ASTM D790
Flexural Modulus, 6.4 mm	3510	MPa	ASTM D790
<b>IMPACT</b>			
FOAM - IMPACT 6.4 mm Wt Reduction	10	%	-
Izod Impact, unnotched, 23°C	854	J/m	ASTM D4812
Falling Dart Impact, 23°C	46	J	SABIC method
<b>THERMAL</b>			
FOAM - THERMAL 6.4mm Wt Reduction	10	%	-
HDT, 0.45 MPa, 6.4 mm, unannealed	140	°C	ASTM D648
HDT, 1.82 MPa, 6.4 mm, unannealed	133	°C	ASTM D648
CTE, -40°C to 95°C, flow	3.24E-05	1/°C	ASTM E831
Specific Heat	1.19	J/g·°C	ASTM C351
Thermal Conductivity	0.13	W/m·°C	ASTM C177
Relative Temp Index, Elec	80	°C	UL 746B
Relative Temp Index, Mech w/impact	80	°C	UL 746B
Relative Temp Index, Mech w/o impact	80	°C	UL 746B
<b>PHYSICAL</b>			
FOAM - PHYSICAL 6.4mm Wt Reduction	10	%	-
Specific Gravity	1.25	-	ASTM D792
Specific Gravity, foam molded	1.12	-	ASTM D792
Water Absorption, (23°C/24hrs)	0.16	%	ASTM D570
Water Absorption, (23°C/Saturated)	0.32	%	ASTM D570
Mold Shrinkage, flow, 6.4 mm	0.4 – 0.6	%	SABIC method
<b>ELECTRICAL</b>			
FOAM - ELECTRICAL 6.4 mm Wt Reduction	20	%	-
Volume Resistivity	2.4E+17	Ω.cm	ASTM D257
Surface Resistivity	>1.1E+17	Ω	ASTM D257
Relative Permittivity, 100 Hz	2.45	-	ASTM D150
Relative Permittivity, 1 MHz	2.4	-	ASTM D150
Dissipation Factor, 100 Hz	0.0013	-	ASTM D150

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
Dissipation Factor, 1 MHz	0.0065	-	ASTM D150
Arc Resistance, Tungsten {PLC}	7	PLC Code	ASTM D495
High Voltage Arc Track Rate {PLC}	4	PLC Code	UL 746A
Comparative Tracking Index (UL) {PLC}	3	PLC Code	UL 746A
FLAME CHARACTERISTICS			
UL Yellow Card Link	<a href="#">E121562-220929</a>	-	-
FOAM - Flame Class Minimum Density	0.85	g/cm <sup>3</sup>	-
UL Recognized, 94V-0 Flame Class Rating	2.99	mm	UL 94
UL Recognized, 94-5VA Flame Class Rating	2.99	mm	UL 94
STRUCTURAL FOAM MOLDING			
Blowing Agent, Physical System	Nitrogen	-	
Blowing Agent, Chemical System	FLC95	-	
Drying Time (Blowing Agent)	4	Hrs	
Drying Temperature (Blowing Agent)	105	°C	
Concentration Range (Blowing Agent)	3 – 5	%	
Recommended Concentration (Blowing Agent)	1.5	%	
Drying Temperature (Resin)	120	°C	
Drying Time (Resin)	3 – 4	Hrs	
Drying Time (Resin, Cumulative)	48	Hrs	
Melt Temperature	290 – 315	°C	
Nozzle Temperature	270 – 295	°C	
Front Temperature	295 – 310	°C	
Middle Temperature	295 – 310	°C	
Rear Temperature	255 – 265	°C	
Mold Temperature	70 – 95	°C	

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.