

# ULTEM™ RESIN 1040A

REGION AMERICAS

## DESCRIPTION

Transparent, high flow Polyetherimide

## TYPICAL PROPERTY VALUES

Revision 20230607

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>MECHANICAL</b>			
Tensile Stress, yld, Type I, 5 mm/min	96	MPa	ASTM D638
Tensile Strain, brk, Type I, 5 mm/min	10	%	ASTM D638
Tensile Modulus, 5 mm/min	3340	MPa	ASTM D638
Flexural Stress, yld, 2.6 mm/min, 100 mm span	158	MPa	ASTM D790
Flexural Modulus, 2.6 mm/min, 100 mm span	3505	MPa	ASTM D790
<b>IMPACT</b>			
Izod Impact, unnotched, 23°C	470	J/m	ASTM D4812
Izod Impact, notched, 23°C	16	J/m	ASTM D256
Gardner, 23°C	7	J	ASTM D3029
<b>THERMAL</b>			
HDT, 1.82 MPa, 6.4 mm, unannealed	196	°C	ASTM D648
<b>PHYSICAL</b>			
Specific Gravity	1.27	-	ASTM D792
Mold Shrinkage, flow, 3.2 mm	0.5 – 0.7	%	SABIC method
Melt Flow Rate, 295°C/6.6 kgf	6.7	g/10 min	ASTM D1238
Melt Flow Rate, 337°C/6.6 kgf	77	g/10 min	ASTM D1238

## ADDITIONAL PRODUCT NOTES

No PFAS intentionally added: The grade listed in this document does not contain PFAS intentionally added during Seller's manufacturing process and is not expected to contain unintentional PFAS impurities. Each user is responsible for evaluating the presence of unintentional PFAS impurities.

## MORE INFORMATION

For curve data and CAE cards, please visit and register at <https://materialfinder.sabic-specialties.com>

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.